

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
21 October 2004 (21.10.2004)

PCT

(10) International Publication Number
WO 2004/089852 A1

(51) International Patent Classification:
// (C04B 40/00, 24:26, 24:32, 24:42)

C04B 40/00

(74) Common Representative: CONSTRUCTION RE-
SEARCH & TECHNOLOGY GMBH; Patente, Marken,
Dr.-Albert-Frank-Strasse 32, 83308 Trostberg (DE).

(21) International Application Number:

PCT/EP2004/002255

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MY, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.

(22) International Filing Date: 5 March 2004 (05.03.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:

0307948.0

7 April 2003 (07.04.2003) GB

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), Euro-
pean (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR,
GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK,
TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,
ML, MR, NE, SN, TD, TG).

(71) Applicant (for all designated States except US):
CONSTRUCTION RESEARCH & TECHNOL-
OGY GMBH [DE/DE]; Patente, Marken, Dr.-Al-
bert-Frank-Strasse 32, 83303 Trostberg (DE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): ZAMPINI, Davide
[DE/DE]; Hoeweg 4, CH-2552 Orpun (CH). WEIBEL,
Martin [CH/CH]; Meientalstrasse 67, CH-8048 Zürich
(CH). WALLISER, André [CH/CH]; Vercinshausstrasse
5, CH-4133 Pratteln (CH). OPPINGER, Max [CH/CH];
Burgeldermattweg 59, CH-4123 Allschwil (CH).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.



WO 2004/089852 A1

(54) Title: COMPOSITION

(57) Abstract: A composition for improving the properties of a cementitious composition comprises a fluid blend of at least one polyalkylene oxide, at least one aqueous paraffin emulsion, at least one siloxane and, if necessary for fluidity, water.

30 where m and n are independently from 1-2000, preferably from 1-500 and more preferably from 1-200, a, b, and c are independently either 0 or 1 and X, Y and Z are selected from

-O-;

-O-(CH₂)₁₋₃₀-, this moiety being at least one of linear, branched and containing at least one ring;

5 -(CH₂)₁₋₃₀-, this moiety being at least one of linear, branched and containing at least one ring;

-CH₂-CH₂-CH₂-O-;

-CH₂-CH₂-CH₂-O-CH₂-CHOH-CH₂-;

-CH₂-CH₂-CH₂-O-CH₂-CHOH-CH₂-O-;

-CH₂-CH₂-CH₂-O-CH₂-CHOH-CH₂-N-;

10

and R, R' and R'' are independently selected from at least one of hydrogen, C₁₋₁₀₀ alkyl, C₆₋₃₀ aryl, C₇₋₃₀ aralkyl; C₇₋₃₀ alkaryl; C₁₋₃₀ hydroxyalkyl; C₃₋₂₀₀ polyhydroxyalkyl; polyether consisting of from 2-200 identical or different C₁₋₁₅ oxyalkylene units; C₁₋₃₀ aminoalkyl; polyiminopolyalkylene having from 1-20 identical or different C₂₋₁₅ alkylene units; polyiminopolyoxyalkylene having from 1-20 identical or different C₂₋₁₅ oxyalkylene units; C₃₋₃₀ quaternary ammonium, optionally completely or partially ionised with at least one anion; C₄₋₃₀ betaine; carboxyl, optionally completely or partially ionised with any suitable cation; C₄₋₃₀ polycarboxyalkyl, optionally completely or partially ionised with at least one cation; sulpho group, optionally completely or partially ionised with at least one cation; thiosulpho group, optionally completely or partially ionised with at least one cation; epoxide group; glycidyl; acrylate; C₁₋₃₀ ester; polyester consisting of from 2-200 C₂₋₁₅ diacid and diester monomer units; and esters of inorganic acids, all alkyl chains being at least one of linear, branched and comprising at least one ring.

25 A more preferred class of siloxane compounds comprises those of Formula I in which a, b, and c are all 1 and X, Y and Z are selected from

-O-(CH₂)₁₋₃₀-, this moiety being linear or branched;

30 -(CH₂)₁₋₃₀-, this moiety being linear or branched;

-CH₂-CH₂-CH₂-O-CH₂-CHOH-CH₂-;

and R, R' and R'' are independently selected from at least one of hydrogen; hydroxy; polyether consisting of from 2-200 identical or different C₂₋₆ oxyalkylene units, with the proviso that, if there is present more than one type of oxyalkylene unit, there shall be present at least two of each unit; C₃₋₃₀ quaternary ammonium, optionally completely or partially ionised with at least one anion; C₄₋₃₀ betaine; carboxyl, optionally completely or partially ionised with at least one cation; sulpho group, optionally completely or partially ionised with at least one cation; thiosulpho group, optionally completely or partially ionised with at least one cation; glycidyl; and acrylate; all alkyl chains being at least one of linear, branched and comprising at least one ring.

10

An even more preferred class of siloxane compounds comprises those of Formula I in which m and n are independently selected from 1-200, a, b, and c are all 1 and X, Y and Z are selected from

15

-O-(CH₂)₁₋₁₂;
 -(CH₂)₁₋₁₂;
 -CH₂-CH₂-CH₂-O-CH₂-CHOH-CH₂;

20

and R, R' and R'' are independently selected from at least one of hydrogen; hydroxy; polyether consisting of from 2-200 identical or different C₂₋₆ oxyalkylene units, with the proviso that, if there is present more than one type of oxyalkylene unit, there shall be present at least two of each unit; C₃₋₃₀ quaternary ammonium, optionally completely or partially ionised with at least one anion; C₄₋₃₀ betaine; carboxyl, optionally completely or partially ionised with at least one cation; glycidyl; and acrylate; all alkyl chains being capable of being linear or branched.

25

An even more preferred class of siloxane compounds comprises those of Formula I in which m is from 1-30 and n is from 1-100, a, b, and c are all 1 and X, Y and Z are selected from

30

-O-(CH₂)₁₋₆;
 -(CH₂)₁₋₆;



and R, R' and R'' are independently selected from at least one of hydrogen; hydroxy; polyether consisting of from 2-200 identical or different C₂₋₆ oxyalkylene units, with the proviso that, if there is present more than one type of oxyalkylene unit, there shall be present at least two of each unit; C₃₋₂₀ quaternary ammonium, optionally completely or partially ionised with at least one anion; C₄₋₁₀ betaine and carboxyl, optionally completely or partially ionised with at least one cation; all alkyl chains being capable of being linear or branched.

10

The siloxanes hereinabove described may be any such material known to the art. Such materials are well known to the art for a variety of purposes, one of these being as antifoams in various industries. The preferred materials are those where R and R' are methyl or ethyl, n is from 5-200, more preferably from 10-150 and most preferably from 40-100, and m is from 1-100, more preferably from 2-40 and most preferably from 5-10.

15

The two different types of siloxane units may be arranged randomly or in blocks on the molecule. It is possible to utilise more than one type of moiety R''. Examples of R'' include ethylene oxide – propylene oxide copolymers of from 10 to 100 units.

20

The siloxanes that are useful in the present invention may either be incorporated into a dry cementitious composition, or they may be added to such a composition when it is mixed with water immediately prior to placement. The quantity required depends on the type of cement and the precise nature of the siloxane, but a typical range of weight proportions is from 0.05%-20% by weight of the weight of the cement, more preferably from 0.1-5%, even more preferably from 0.1-2% and most preferably from 0.2-1%.

25

In a further embodiment of the invention, the siloxane may be used in conjunction with hydrophobic, finely-divided silica. This can be added to the composition separately from the siloxane, but it is preferred that it be incorporated into the siloxane by, for example, blending or mixing. The quantity of silica can be up to 20% by weight of the siloxane, preferably no more than 10%. In a yet further embodiment of the invention, the siloxane

30

may additionally contain emulsifier. Any suitable emulsifiers may be used in art-recognised quantities. Some commercially-available emulsifiers already contain emulsifier, so addition may be unnecessary.

Preferably the polyalkylene oxide is polyethylene oxide. The weight-average molecular weight is from 100,000-8,000,000, preferably from 2,000,000-5,000,000.

There are many types of paraffin emulsions available and any of these may be used in the working of the invention. By "paraffin emulsion" is meant an aqueous emulsion of a higher alkane having a fusion point above ambient temperature, which upon drying of the emulsion does not form a film in the sense that a paint forms a film (see also Römpp "Chemie Lexikon", 9th edition (Thieme Verlag 1989), volume 1, page 102, the contents of which are incorporated herein by reference). The emulsion may be stabilised by any convenient means, but it is preferable to use an ionically-emulsified (preferably anionically-stabilised) paraffin mixture (fusion point of 45-51°C) with a particle size of less than 2µm. Examples of such paraffin emulsions are "Mobilcer" 55 or "Mulrex" 62 from Mobil and "Ubatol" FPG 860 from Cray Valley and "Tecol" BC 60/40 from Trüb Emulsion Chemie.

The concentrations of the three ingredients and water in the chemical composition are shown below (as percentages by weight of the total composition). In some cases, the blend of the three ingredients is sufficiently fluid to make any water unnecessary, but generally some water is necessary, sometimes in relatively high proportion (when, for example, the polyethylene oxide is of high molecular weight).

	<u>Widest limits</u>	<u>preferred</u>	<u>more preferred</u>
siloxane	5-60	10-50	20-40
paraffin wax	10-70	20-60	30-50
polyethylene oxide	0.1-5	0.2-2	0.5-1.5
water	0-80	20-70	30-50

The three materials may be mixed into a dry cement, mortar or concrete mix, to which water need only be added, or they may be added individually or collectively in any

combination to a cementitious mix when water is being added, prior to final use. It is preferred to combine the three (with water if necessary) in a single admixture. The material has a long shelf life and is ready for use without any prior preparation.

In use, the chemical composition is added in a quantity of from 0.01 – 100% by weight on cement. The water content may be varied over wide limits, depending on the effect
5 desired. It is preferred to have relatively little water content, i.e., preferably less than 50% by weight of the composition. In such a case, the preferred quantity by weight on cement is from 0.05-10%, more preferably from 0.1-3% and most preferably from 0.2-2%.

10 The use of the composition has a considerable and highly beneficial effect on any cementitious composition in which it is incorporated. Not only is the shrinkage and cracking decreased or even eliminated, as hereinabove described, but there may also be noticeable improvements in properties such as freeze-thaw resistance and permeability, and there can also be a significant plasticising effect. The nature and extent of
15 improvement will depend on the type of cementitious mix and the natures and concentrations of the various constituent raw materials, but there is always some enhancement. The invention therefore also provides a method of modifying the properties of a cementitious composition, comprising adding to a fluid cementitious mix a chemical composition as hereinabove described. The invention further provides a cementitious
20 composition having improved properties, which composition comprises a chemical composition as hereinabove described.

In addition to the one or three materials hereinabove described, there can also be added to the cementitious mix materials known to the art for the performance of particular
25 functions, in art-recognised quantities. Such materials include (but are not limited to) plasticisers and superplasticisers, accelerators, antifreeze agents, pigments, air-entraining agents, retarders and reinforcing fibres of metal, glass or polymer.

The invention is further described with reference to the following non-limiting examples.

30

A number of materials are tested in a standard concrete mix, the mix design being as follows:

Cement 450 kg/m³

Aggregate

0-4 mm 990 kg/m³
 4-8 mm 660 kg/m³

Water-to-cement ratio = 0.47

The materials tested are as follows:

10

Admixture 1 – a blend of a commercial paraffin wax emulsion (“Tecol” BC 60/40 from Trüb Emulsion Chemie) and a polyethylene oxide of MW 4,000,000 (“Polyox” (trade mark) 301 from Union Carbide), the blend containing 40% by weight paraffin emulsion and 1% polyethylene oxide

15 Admixture 2 – Admixture 1 + siloxane (a polyether siloxane wherein m+n=75, having on average per molecule 6.5 ethylene oxide/propylene oxide side chains of MW 1800)

Admixture 3 – a commercial neopentyl glycol-based shrinkage reducing agent.

20 Admixture 4 – a commercial shrinkage-reducing agent which is a blend of polyoxyalkylene ethers.

In all cases, 1% admixture by weight of cement is used, except in the case of Admixture 2, where 1% each of Admixture 1 and siloxane are used.

25 The drying free shrinkage is measured by German Standard Test Method DIN 52 450.

The results are shown in the following table:

Drying free shrinkage (mm/m)					
Age (days)	No admixture	Admixture 1	Admixture 2	Admixture 3	Admixture 4
1	0	0	0	0	0
3	0.068	0.077	-0.044	0.026	-0.011
7	0.173	0.177	-0.004	0.129	0.046
14	0.233	0.226	0.028	0.203	0.127
21	0.283	0.294	0.066	0.234	0.157
28	0.328	0.329	0.102	0.272	0.213


38	0.365	0.359	0.121	0.282	0.223
58	0.416	0.423	0.193	0.35	0.281
67	0.433	0.428	0.233	0.387	
87	0.473	0.485	0.271	0.389	0.341

It can be seen that the performance of Admixture 2 is appreciably better than that of the other admixtures. It is particularly noteworthy that the shrinkage performance of

5 Admixture 1 goes from being the worst to the best, when it is augmented by siloxane to give Admixture 2. In addition, it is found that the cementitious mix flows better and that the final cementitious composition is less permeable to water than an identical composition but without the chemical composition.

Claims:

1. A composition for improving the properties of a cementitious composition, comprising a fluid blend of
 - (i) at least one polyalkylene oxide, the alkylene oxide units being ethylene and propylene oxides;
 - (ii) at least one aqueous paraffin emulsion; and
 - (iii) at least one siloxane compound that is at least one of liquid and soluble in at least one of water and aqueous alkali.
2. A composition according to claim 1, in which the siloxane is selected from those that correspond to the general formula I:




where m and n are independently from 1-2000, preferably from 1-500 and more preferably from 1-200, a, b, and c are independently either 0 or 1 and X, Y and Z are selected from

-0-;

-O-(CH₂)₁₋₃₀-, this moiety being at least one of linear, branched and containing at least one ring;


-(CH₂)₁₋₃₀-, this moiety being at least one of linear, branched and containing at least one ring;

$$-\text{CH}_2-\text{CH}_2-\text{CH}_2-\text{O}-;$$



5 and R, R' and R'' are independently selected from at least one of hydrogen, C₁₋₁₀₀ alkyl, C₆₋₃₀ aryl, C₇₋₃₀ aralkyl; C₇₋₃₀ alkaryl; C₁₋₃₀ hydroxyalkyl; C₃₋₂₀₀ polyhydroxyalkyl; polyether consisting of from 2-200 identical or different C₁₋₁₅ oxyalkylene units; C₁₋₃₀ aminoalkyl; polyiminopolyalkylene having from 1-20 identical or different C₂₋₁₅ alkylene units; polyiminopolyoxyalkylene having from 1-20 identical or different C₂₋₁₅ oxyalkylene units; C₃₋₃₀ quaternary ammonium, optionally completely or partially ionised with at least one anion; C₄₋₃₀ betaine; carboxyl, optionally completely or partially ionised with any suitable cation; C₄₋₃₀ polycarboxyalkyl, optionally completely or partially ionised with at least one cation; sulpho group, optionally completely or partially ionised with at least one cation; thiosulpho group, optionally completely or partially ionised with at least one cation; epoxide group; glycidyl; acrylate; C₁₋₃₀ ester; polyester consisting of from 2-200 C₂₋₁₅ diacid and diester monomer units; and esters of inorganic acids, all alkyl chains being at least one of linear, branched and comprising at least one ring.

20 3. A composition according to claim 1 or claim 2, in which the siloxane is selected from those of Formula I in which a, b, and c are all 1 and X, Y and Z are selected from



30 and R, R' and R'' are independently selected from at least one of hydrogen; hydroxy; polyether consisting of from 2-200 identical or different C₂₋₆ oxyalkylene units, with the proviso that, if there is present more than one type of oxyalkylene unit, there shall be present at least two of each unit; C₃₋₃₀ quaternary ammonium, optionally completely or partially ionised with at least one anion; C₄₋₃₀ betaine;

carboxyl, optionally completely or partially ionised with at least one cation; sulpho group, optionally completely or partially ionised with at least one cation; thiosulpho group, optionally completely or partially ionised with at least one cation; glycidyl; and acrylate; all alkyl chains being at least one of linear, branched and comprising at least one ring.

4. A composition according to any one of claims 1-3, in which the siloxane is selected from those of Formula I in which m and n are independently selected from 1-200, a, b, and c are all 1 and X, Y and Z are selected from

-O-(CH₂)₁₋₁₂-;

-(CH₂)₁₋₁₂-;

-CH₂-CH₂-CH₂-O-CH₂-CHOH-CH₂-;

- and R, R' and R'' are independently selected from at least one of hydrogen; hydroxy; polyether consisting of from 2-200 identical or different C₂₋₆ oxyalkylene units, with the proviso that, if there is present more than one type of oxyalkylene unit, there shall be present at least two of each unit; C₃₋₃₀ quaternary ammonium, optionally completely or partially ionised with at least one anion; C₄₋₃₀ betaine; carboxyl, optionally completely or partially ionised with at least one cation; glycidyl; and acrylate; all alkyl chains being capable of being linear or branched.

5. A composition according to any one of claims 1-4, in which the siloxane is selected from those of Formula I in which m is from 1-30 and n is from 1-100, a, b, and c are all 1 and X, Y and Z are selected from

-O-(CH₂)₁₋₆-;

-(CH₂)₁₋₆-;

-CH₂-CH₂-CH₂-O-CH₂-CHOH-CH₂-;

and R, R' and R'' are independently selected from at least one of hydrogen; hydroxy; polyether consisting of from 2-200 identical or different C₂₋₆ oxyalkylene

units, with the proviso that, if there is present more than one type of oxyalkylene unit, there shall be present at least two of each unit; C₃₋₂₀ quaternary ammonium, optionally completely or partially ionised with at least one anion; C₄₋₁₀ betaine and carboxyl, optionally completely or partially ionised with at least one cation; all alkyl chains being capable of being linear or branched.

6. A composition according to any one of claims 1-5 in which the polyalkylene oxide is polyethylene oxide.
- 10 7. A composition according to any one of claims 1-6 in which the weight-average molecular weight of the polyalkylene oxide is 100,000-8,000,000, preferably 2,000,000-5,000,000.
- 15 8. A composition according to any one of claims 1-7 in which the paraffin emulsion is an ionically-emulsified paraffin mixture with a fusion point of 45-51°C and a particle size of less than 2µm.
- 20 9. A method of modifying the properties of a cementitious composition, comprising adding to a fluid cementitious mix a composition according to any one of claims 1-8.
10. A cementitious mix having improved properties, which composition comprises a chemical composition according to claims 1-8.

INTERNATIONAL SEARCH REPORT

International Application No.
PCT/EP2004/002255

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 C04B40/00 //(C04B40/00,C04B24:26,C04B24:32,C04B24:42)														
According to International Patent Classification (IPC) or to both national classification and IPC														
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 7 C04B														
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched														
Electronic data base consulted during the International search (name of data base and, where practical, search terms used) EPO-Internal, PAJ														
C. DOCUMENTS CONSIDERED TO BE RELEVANT <table border="1"> <thead> <tr> <th>Category *</th> <th>Citation of document, with indication, where appropriate, of the relevant passages</th> <th>Relevant to claim No.</th> </tr> </thead> <tbody> <tr> <td>X</td> <td>EP 0 641 746 A (SANDOZ AG ; SANDOZ LTD (CH); SANDOZ AG (DE)) 8 March 1995 (1995-03-08) the whole document</td> <td>1,6-10</td> </tr> <tr> <td>Y</td> <td>-----</td> <td>2-5</td> </tr> <tr> <td>Y</td> <td>PATENT ABSTRACTS OF JAPAN vol. 1997, no. 05, 30 May 1997 (1997-05-30) & JP 9 020540 A (SHIN ETSU CHEM CO LTD), 21 January 1997 (1997-01-21) the whole document -----</td> <td>2-5</td> </tr> </tbody> </table>			Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.	X	EP 0 641 746 A (SANDOZ AG ; SANDOZ LTD (CH); SANDOZ AG (DE)) 8 March 1995 (1995-03-08) the whole document	1,6-10	Y	-----	2-5	Y	PATENT ABSTRACTS OF JAPAN vol. 1997, no. 05, 30 May 1997 (1997-05-30) & JP 9 020540 A (SHIN ETSU CHEM CO LTD), 21 January 1997 (1997-01-21) the whole document -----	2-5
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.												
X	EP 0 641 746 A (SANDOZ AG ; SANDOZ LTD (CH); SANDOZ AG (DE)) 8 March 1995 (1995-03-08) the whole document	1,6-10												
Y	-----	2-5												
Y	PATENT ABSTRACTS OF JAPAN vol. 1997, no. 05, 30 May 1997 (1997-05-30) & JP 9 020540 A (SHIN ETSU CHEM CO LTD), 21 January 1997 (1997-01-21) the whole document -----	2-5												
<input type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.														
* Special categories of cited documents : *A* document defining the general state of the art which is not considered to be of particular relevance *E* earlier document but published on or after the international filing date *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) *O* document referring to an oral disclosure, use, exhibition or other means *P* document published prior to the international filing date but later than the priority date claimed *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. *C* document member of the same patent family														
Date of the actual completion of the international search 8 June 2004		Date of mailing of the international search report 18/06/2004												
Name and mailing address of the ISA European Patent Office, P.B. 5816 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer Gattinger, I												

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP2004/002255

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0641746	A	08-03-1995	AT 227249 T	15-11-2002
			AU 673278 B2	31-10-1996
			AU 7166594 A	23-03-1995
			DE 69431645 D1	12-12-2002
			DE 69431645 T2	10-07-2003
			EP 0641746 A2	08-03-1995
			ES 2136683 T3	16-05-2003
			JP 7309652 A	28-11-1995
			NO 943287 A	09-03-1995
			SG 52787 A1	25-05-1999
			US 5674929 A	07-10-1997
JP 9020540	A	21-01-1997	NONE	